



# FE 9050 S Technical Data



FE-INTERLININGS

FE-INTERLININGS

<b>1. Specification</b>							
Supplier Article No.	<b>FE-9050 S</b>						
Color(s)	<b>BLEACHED WHITE - BLACK</b>						
Origin	<b>CHINA</b>						
Supplier Name	<b>TELPA TEKSTIL URUNLERI DIS TIC.LTD.STI.</b>						
Width (cm)	<b>150 CM</b>						
Thickness (mm)							
Roll length (rm/roll)	<b>100 / ROLL</b>						
<b>2. Construction</b>							
Grey fabric							
Composition (%)	<b>POLIESTER</b>						
Construction	<b>CIRCULAR KNITTED</b>						
Weight (g/m <sup>2</sup> ) - (A)	<b>FINISHED GOODS : 40</b>						
Yarn							
Yarn Composition (%)	<b>100% POLIESTER</b>						
Yarn Density (thread/inch)	Warp		Weft				
Woven Yarn Count (Denier)	Warp		Weft				
Knit (gauge/inch)	Warp		Weft				
Weft-inserted (gauge/inch)	Warp		Weft				
Coating							
Coating Method	<b>DOUBLE DOT</b>						
Composition (%)			<b>PA+PES</b>				
Dot Size (dot/cm <sup>2</sup> )							
Adhesive Weight (g/m <sup>2</sup> )	Top Dot	<b>10~12gsm</b>	Sub Dot				
Total Adhesive Weight (g/m <sup>2</sup> ) - (B)							
Total Weight (g/m <sup>2</sup> ) (ISO9073-1) = (A + B)							
<b>3. Oeko-tex 100 Standard</b>							
Class	<b>I</b>		Cert. No.				
Valid Until							
<b>4. Formaldehyde</b>							
Japan Law 112 (ppm)							
Other, please specific							
<b>5. Fusing Conditions</b>							
Setting Temperature (°C)							
Fuseline Temperature (°C)	<b>125~130</b>						
Time (second)	<b>10~12</b>						
Pressure	<b>8~10</b>	<b>N/cm<sup>2</sup></b>	<b>Bar</b>	<b>2~2,5</b>	<b>Kg/m<sup>2</sup></b>		
<b>6. Care Labels</b>							
Washing (°C)	<b>40±3</b>		Other				
Bleaching							
Dry clean (P) - P=Perchloroethylene	<b>AVAILABLE</b>						
Prepared by :	<b>TELPA TEKSTIL</b>		Date:	<b>1.08.2019</b>			