



# FE-9030 Technical Data



FE-INTERLININGS

FE-INTERLININGS

<b>1. Specification</b>						
Supplier Article No.	<b>FE-9030</b>					
Color(s)	<b>OFF WHITE - BLEACHED WHITE - BLACK</b>					
Origin	<b>CHINA</b>					
Supplier Name	<b>TELPA TEKSTIL URUNLERI DIS TIC.LTD.STI.</b>					
Width (cm)	<b>150 CM</b>					
Thickness (mm)						
Roll length (rm/roll)	<b>100 / ROLL</b>					
<b>2. Construction</b>						
Grey fabric						
Composition (%)	<b>POLIESTER</b>					
Construction	<b>KNITTED</b>					
Weight (g/m <sup>2</sup> ) - (A)	<b>FINISHED GOODS : 30</b>					
Yarn						
Yarn Composition (%)	Warp	<b>100% POLIESTER</b>		Weft	<b>100% POLIESTER</b>	
Yarn Density (thread/inch)	Warp	<b>30 D</b>		Weft	<b>30 D</b>	
Woven Yarn Count (Denier)	Warp			Weft		
Knit (gauge/inch)	Warp			Weft		
Weft-inserted (gauge/inch)	Warp			Weft		
Coating						
Coating Method	<b>PA</b>					
Composition (%)		<b>100%</b>				
Dot Size (dot/cm <sup>2</sup> )						
Adhesive Weight (g/m <sup>2</sup> )	Top Dot	<b>8~10gsm</b>		Sub Dot		
Total Adhesive Weight (g/m <sup>2</sup> ) - (B)						
Total Weight (g/m <sup>2</sup> ) (ISO9073-1) = (A + B)						
<b>3. Oeko-tex 100 Standard</b>						
Class				Cert. No.	<b>114469</b>	
Valid Until						
<b>4. Formaldehyde</b>						
Japan Law 112 (ppm)						
Other, please specific						
<b>5. Fusing Conditions</b>						
Setting Temperature (°C)						
Fuseline Temperature (°C)	<b>125~140</b>					
Time (second)	<b>10~15</b>					
Pressure	<b>8~10</b>	<b>N/cm<sup>2</sup></b>		<b>Bar</b>	<b>1,5~2</b>	<b>Kg/m<sup>2</sup></b>
<b>6. Care Labels</b>						
Washing (°C)	<b>40±3</b>		Other			
Bleaching						
Dry clean (P) - P=Perchloroethylene	<b>AVAILABLE</b>					
Prepared by :	<b>TELPA TEKSTIL</b>			Date:	<b>1.08.2019</b>	